















## SPECIFICATIONS

	<b>GEOLOGY</b>	Naturally irregular bedface pieces from the quarry
	<b>TYPE</b>	100% Bedface
	<b>PATTERN</b>	Mosaic
	<b>HEIGHTS</b>	Irregular up to 16" across (Full Bed & Thin Veneer)
	<b>LENGTHS</b>	Random, up to 16"
	<b>DEPTHS</b>	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer)
	<b>COLORS</b>	Light and warm medium grays.
	<b>COVERAGE</b>	Full Bed Depth Veneer: 30-40 Square Feet Per Ton
	<b>WEIGHT</b>	13.4 lbs. per square foot (Thin Veneer)
	<b>FLATS</b>	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	<b>CORNERS</b>	10 l/f Box, 100 l/f Crate, 100 l/f Pallet
	<b>NOTES</b>	

### ASTM C-97

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

### ASTM C-170

Parallel to Rift, Dry	36100 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

### ASTM C-99

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

### ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi



**GOLD QUARRY**  
 ANSI/NSC 373-2013  
 C0290908-101



**GOLD FABRICATOR**  
 ANSI/NSC 373-2013  
 C0289215-101