















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	60% Bedface, 40% Split Face
	PATTERN	2:1 Sawn Course Heights Dimensional Ashlar
	HEIGHTS	2-1/4" (20%), 5" (40%), 7-3/4" (30%), 10-1/2" (10%): Full Bed & Thin Veneer
	LENGTHS	8" - 24" (Thin Veneer, crated/palletized material can exceed 20"); 8"-48" (Full Bed)
	DEPTHS	3/4" to 1-1/4" (Thin Veneer); 3" - 5" Nominal (Full Bed-Depth)
	COLORS	Brown, Buff, Gray-Grey
	COVERAGE	Full Bed Depth Veneer: 35-40 Square Feet Per Ton
	WEIGHT	13.7 lbs. per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	<i>Heritage Dimensional™</i> was also known as the legacy NSVI products, "Cedar Creek", and "Pine Creek". Some photos may still be labeled with the former product names.

ASTM C-97

Water Absorption %	.50 psi
Bulk Specific Gravity	2.79 psi

ASTM C-170

Parallel to Rift, Dry	21300 psi
Parallel to Rift, Wet	20300 psi
Perpendicular to Rift, Dry	29400 psi
Perpendicular to Rift, Wet	29100 psi

ASTM C-99

Parallel to Rift, Dry	2040 psi
Parallel to Rift, Wet	1690 psi

ASTM C-880

Perpendicular to Rift, Dry	
Perpendicular to Rift, Wet	



GOLD QUARRIER
 ANSI/NSC 373-2013
 C0290908-101



GOLD FABRICATOR
 ANSI/NSC 373-2013
 C0289215-101