















SPECIFICATIONS

	GEOLOGY	Limestone
	TYPE	Tumbled, 100% Bedface
	PATTERN	2:1 Dimensional Ashlar
	HEIGHTS	2-1/4" (20%), 5" (50%), 7-3/4" (30%): Thin and Full Veneer
	LENGTHS	8" - 16" (Thin Veneer)
	DEPTHS	3/4" - 1 1/4" (Thin Veneer); 3"-5" Full Veneer
	COLORS	Gray, Buff, Tan
	COVERAGE	35-40 square feet per ton (full veneer)
	WEIGHT	13.4 lbs. per square foot (Thin Veneer)
	FLATS	10 s/f Box; 100 s/f Crate, 180 s/f Crate; 100 s/f Pallet, 180 s/f Crate, 200 s/f Pallet
	CORNERS	10 l/f Box; 100 l/f Crate; 100 l/f pallet
	NOTES	Tumbled version of Fond du Lac Dimensional .

ASTM C-97

Water Absorption %	.31 psi
Bulk Specific Gravity	2.83 psi

ASTM C-170

Parallel to Rift, Dry	36100 psi
Parallel to Rift, Wet	32000 psi
Perpendicular to Rift, Dry	35800 psi
Perpendicular to Rift, Wet	30000 psi

ASTM C-99

Parallel to Rift, Dry	3770 psi
Parallel to Rift, Wet	3500 psi

ASTM C-880

Perpendicular to Rift, Dry	1780 psi
Perpendicular to Rift, Wet	1730 psi

